

PAPEL FILM ESTIRABLE

by **SAFE PALLET**®

100% ecológico y reciclable



**LA ALTERNATIVA 100% ECOLÓGICA
AL FILM DE PLÁSTICO ESTIRABLE**


FICHA TÉCNICA PFE60	UNIDAD	VALOR TÍPICO	NORMA
GRAMAJE	gr/m ²	60	UNE-EN-ISO 536
ESPESOR	mm	0,194	UNE-EN-ISO 536
CARGA ROTURA SL	kg/cm	1,42	UNE-EN-ISO 1924
CARGA ROTURA ST	kg/cm	1,33	UNE-EN-ISO 1924
ALARGAMIENTO SL	%	61,1	UNE-EN-ISO 1924
ALARGAMIENTO ST	%	4,6	UNE-EN-ISO 1924
METROS SIN PRE-ESTIRO	m	330	
METROS CON PRE-ESTIRO	m	445	
PESO	kg	9,7	

SL: Sentido Longitudinal
ST: Sentido Transversal



ACONDICIONAMIENTO DE MUESTRAS: ISO 554 - 1976 (23°C ± 1°C; 50% ± 2%)
CONFORME A LA RECOMENDACIÓN XXXVI DE LA REGLAMENTACIÓN BFR PARA SU USO EN ALIMENTACIÓN

filmpapelestirable.com



PAPER STRETCH FILM

by **SAFE PALLET**®

100% eco-friendly and recyclable



THE ECO-FRIENDLY ALTERNATIVE TO STRETCH FILM

SPECIFICATIONS PFE60	UNIT	TYPICAL VALUE	NORMATIVE
SUPPORT	gr/m ²	60	UNE-EN-ISO 536
THICKNESS	mm	0,194	UNE-EN-ISO 536
BREAKING LOAD LD	kg/cm	1,42	UNE-EN-ISO 1924
BREAKING LOAD CD	kg/cm	1,33	UNE-EN-ISO 1924
STRETCHING LD	%	61,1	UNE-EN-ISO 1924
STRETCHING CD	%	4,6	UNE-EN-ISO 1924
METERS WITHOUT STRETCH	m	330	
METERS WITH STRETCH	m	445	
WEIGHT	kg	9,7	

LD: Longitudinal Direction
CD: Cross Direction



SAMPLE CONDITIONING: ISO 554 - 1976 (23°C ± 1°C; 50% ± 2%)
IN ACCORDANCE WITH XXXVI RECOMMENDATION OF BFR REGULATION FOR USE WITH FOOD

paperstretchfilm.com

Avenida Mediterráneo, 137, 12200, Onda (Castellón) comercial@safepallet.es - 964 62 61 63